

PREST® PAVERS

Paver Color and Finish	Reflect. Average	Emitt. Average	SRI	Color
Brown/Tudor®	.0262	0.92	28.0	RB
Cream/ Tudor®	0.33	0.97	39.0	BT
Charcoal/Tudor®	0.24	0.91	25.0	DGG
Charcoal/Heavy Tudor®	0.27	0.89	28.0	DGG
Glacier White/Diamond	0.62	0.96	77.0	WL
Glacier White/Finish #13	0.66	0.93	81.0	WL
Glacier White/Ground	0.60	0.89	72.0	WL
Glacier White/Stipple	0.68	0.93	84.0	WL
Glacier White/Tudor®	0.69	0.94	85.0	WL
Limestone Gray/Tudor®	0.25	0.92	26.0	LMG
Limestone Gray/Ground	0.32	0.88	33.0	LMG
Limestone Gray/Ground Tudor®	0.359	0.90	40.0	LMG
M929/Ground	0.44	0.88	50.0	BT
M929/Tudor®	0.35	0.95	40.0	BT
M1018/Tudor®	0.33	0.90	36.0	RB
M1025/Tudor®	0.344	0.91	38.0	LMG
M1031/Tudor®	0.426	0.91	49.0	WL
M1041/Tudor®	0.271	0.92	29.0	LMG
M1043/Tudor®	0.267	0.97	31.0	RB
M1064/Tudor®	0.29	0.91	31.0	LMG
M1078/Ground	0.43	0.88	48.0	LMG
M1078/Tudor®	0.33	0.95	38.0	LMG
M115/Finish #13	0.36	0.93	41.0	WL
M115/Ground	0.50	0.89	58.0	WL
M115/Tudor®	0.435	0.91	50.0	WL
M1106/Tudor®	0.207	0.92	21.0	LMG
M1109/Ground	0.425	0.83	46.0	LMG
M1119/Ground Tudor®	0.239	0.94	26.0	RB
M1147/Tudor®	0.192	0.91	19.0	DGG
M1186/Tudor®	0.176	0.93	18.0	RB
M1187/Tudor®	0.53	0.96	64.0	WL
M1356/Tudor®	0.33	0.87	34.0	LMG
M1377/Tudor®	0.58	0.92	70.0	WL
M1385/Tudor®	0.249	0.93	27.0	LMG
M1428/Tudor®	0.111	0.87	6.0	DGG
M1428/Finish #13	0.124	0.88	9.0	DGG
M1457/Tudor®	0.317	0.91	35.0	BT
M1636/Finish #13	0.14	0.84	9.0	DGG

PREST® PAVERS

Paver Color and Finish	Reflect. Average	Emitt. Average	SRI	Color
M1676/Finish #13	0.446	0.91	51.0	WL
M1773/Tudor®	0.145	0.97	15.0	DGG
M1807/Finish #13	0.351	0.91	39.0	BT
M1810/Tudor®	0.36	0.90	40.0	BT
M1861/Finish #13	0.29	0.91	31.0	LMG
M1875/Heavy Tudor®	0.49	0.91	57.0	WL
M1931/Finish #13	0.43	0.91	50.0	BT
M1931/Ground	0.43	0.95	51.0	BT
M1934/Finish #13	0.54	0.89	64.0	WL
M1944/Finish #13	0.53	0.92	63.0	WL
M1983/Tudor®	0.528	0.91	63.0	WL
M2031/Tudor®	0.47	0.92	55.0	WL
M2115/Finish 13	0.50	0.88	58.0	WL
M2127/Finish 13	0.64	0.91	78.0	WL
M2129/Finish #13	0.348	0.91	44.0	WL
M2190/Tudor®	0.46	0.93	54.0	BT
M2210/Heavy Tudor®	0.233	0.92	24.0	LMG
M2224/Tudor®	0.266	0.91	28.0	BT
M2240/Finish #12	0.17	0.88	15.0	DGG
M2246/Ground	0.276	0.91	30.0	BT
M2310/Tudor®	0.392	0.91	44.0	WL
M2378/Ground	0.21	0.88	20.0	DGG
M2378/Tudor®	0.37	0.88	40.0	LMG
M2379/Ground	0.44	0.97	53.0	BT
M2380/Ground	0.55	0.89	65.0	WL
M2380/Tudor®	0.52	0.92	62.0	WL
M2385/Tudor®	0.337	0.97	40.0	LMG
M2397/Finish #13	0.21	0.90	20.0	DGG
M2397/Tudor®	0.16	0.95	16.0	DGG
M2399/Ground	0.218	0.91	22.0	DGG
M2399/Tudor	0.28	0.89	29.0	DGG
M2400/Ground	0.25	0.93	27.0	DGG
M2400/Tudor®	0.37	0.89	41.0	RB
M2401/Ground	0.31	0.95	35.0	RB

The initial SRI of 85 for this paver material meets the minimum initial SRI value for low-sloped roofs

Color Group Codes

WL = White to Light Buffs and Grays
 BT = Buff to Tan
 LMG = Light Gray to Medium Gray
 DGG = Dark Gray to Green
 RB = Red to Brown

PREST® PAVERS

Paver Color and Finish	Reflect. Average	Emitt. Average	SRI	Color
M2381/Ground	0.51	0.90	60.0	WL
M2381/Tudor®	0.53	0.94	64.0	WL
M2450/Ground	0.34	0.89	37.0	LMG
M2450/Tudor®	0.33	0.94	37.0	LMG
M2524/Tudor®	0.463	0.89	53.0	BT
M2545/Heavy Tudor®	0.266	0.92	29.0	DGG
M2639/Tudor®	0.37	0.92	42.0	BT
M2649/Ground	0.38	0.90	43.0	BT
M2649/Ground Tudor®	0.40	0.90	45.0	BT
M2649/Heavy Tudor®	0.33	0.87	35.0	BT
M2732/Heavy Tudor®	0.38	0.89	43.0	BT
M2738/Tudor®	0.227	0.92	24.0	DGG
M2810/Finish #12	0.19	0.91	18.0	DGG
M2922/Tudor®	0.38	0.92	43.0	LMG
M2953/Tudor®	0.316	0.93	35.0	WL
M3048/Finish #13	0.595	0.92	72.0	WL
M3055/Tudor®	0.31	0.92	34.0	LMG
M3141/Ground	0.36	0.87	39.0	RB
M3165/Ground	0.41	0.88	45.0	BT
M3174/Ground	0.45	0.91	52.0	BT
M3249/Tudor®	0.225	0.90	22.0	LMG
M3260/Tudor®	0.311	0.90	34.0	LMG
M3294/Finish #13	0.441	0.91	51.0	RB
M3311/Tudor®	0.276	0.90	29.0	LMG
M3403/Ground Tudor®	0.368	0.94	43.0	LMG
M3461/Heavy Tudor®	0.459	0.90	53.0	LMG
M3574/Finish #13	0.193	0.91	19.0	RB
Natural/Tudor®	0.39	0.93	45.0	LMG
Natural/Finish #13	0.392	0.91	44.0	LMG
Quarry Red/Tudor®	0.28	0.90	29.0	RB
Quarry Red/Natural	0.19	0.90	17.0	RB
Red 15/Tudor®	0.36	0.92	41.0	RB
Super Black/Tudor®	0.151	0.92	14.0	DGG
Tan/Tudor®	0.30	0.93	33.0	BT
Tan/Finish #13	0.253	0.91	27.0	BT
Antietam/Heavy Tudor®	0.374	0.95	43.0	BT
Antietam/Ground	0.46	0.90	53.0	BT

ASPHALT BLOCK

Asphalt Color and Finish	Reflect. Average	Emitt. Average	SRI
A80016/Ground	0.127	0.91	11.0
A80016/Ground Tudor®	0.130	0.91	11.0
A80020/Ground	0.41	0.86	45.0
A80020/Ground Tudor®	0.32	0.87	34.0
A80033/Ground	0.36	0.88	39.0
A80033/Ground Tudor®	0.30	0.89	32.0

SLATEFACE PREST® PAVERS

SlateFace Color and Finish	Reflect. Average	Emitt. Average	SRI	Color
M2343 Tennessee Flagstone/Finish 13	0.30	0.91	32.0	BT
M2374 BlueStone/Finish 13	0.198	0.89	19.0	DGG

DETECTABLE WARNING® PAVERS

SlateFace Color and Finish	Reflect. Average	Emitt. Average	SRI	Color
Charcoal/Natural	0.09	0.89	5.0	DGG

GRANITE PAVERS

Paver Color and Finish	Reflect. Average	Emitt. Average	SRI
Ashford White/Thermal Flamed	0.44	0.87	49.0
Ashford White/Polished	0.33	0.83	33.0
Basalt Black/Thermal Flamed	0.156	0.88	13.0
Butterfly Green/Thermal Flamed	0.20	0.86	17.0
Champagne Mist/Thermal Flamed	0.582	0.92	70.0
Champagne Mist/Polished	0.467	0.84	52.0
Golden Brazil/Thermal Flamed	0.454	0.87	51.0
Leopard Skin/Thermal Flamed	0.334	0.88	36.0
Milky Way/Thermal Flamed	0.345	0.85	36.0
Milky Way/Polished	0.266	0.90	28.0
Rushmore Gray/Thermal Flamed	0.393	0.85	42.0
Rushmore Gray/Polished	0.277	0.89	29.0
Salmon Red/Thermal Flamed	0.36	0.86	38.0
Silver White/Thermal Flamed	0.306	0.80	28.0
White Flower/Thermal Flamed	0.400	0.80	41.0

Color Group Codes

WL = White to Light Buffs and Grays
 BT = Buff to Tan
 LMG = Light Gray to Medium Gray
 DGG = Dark Gray to Green
 RB = Red to Brown

PREST® BRICK

Brick Color and Finish	Reflect. Average	Emitt. Average	SRI	Color
B9115/Natural	0.35	0.91	39.0	LMG
B9115/Tudor®	0.36	0.96	42.0	LMG
B91018/Tudor®	0.146	0.92	13.0	DGG
B91041/Tudor®	0.232	0.94	25.0	LMG
B91064/Tudor®	0.375	0.91	42.0	WL
B91186/Tudor®	0.186	0.92	19.0	RB
B91240/Tudor®	0.35	0.96	41.0	RB
B91356/Tudor®	0.28	0.88	29.0	LMG
B91442/Tudor®	0.452	0.90	52.0	WL
B91561/Tudor®	0.40	0.98	48.0	BT
B91636/Tudor®	0.18	0.87	16.0	DGG
B91685/Tudor®	0.491	0.91	58	DGG
B91763/Tudor®	0.211	0.94	23.0	DGG
B91764/Tudor®	0.193	0.96	21.0	LMG
B91765/Tudor®	0.139	0.94	13.0	DGG
B91775/Ground Tudor®	0.346	0.94	40.0	BT
B91930/Tudor®	0.46	0.92	54.0	WL
B91983/Tudor®	0.48	0.97	58.0	BT
B92034/Tudor®	0.23	0.91	24.0	LMG
B92049/Tudor®	0.38	0.91	43.0	WL
B92115/Tudor®	0.36	0.97	42.0	BT
B92310/Tudor®	0.341	0.91	38.0	LMG
B92620/Tudor®	0.380	0.89	42.0	LMG
B92649/Tumbled	0.23	0.88	22.0	BT
B92715/Tudor®	0.58	0.95	71.0	BT
B92738/Tudor®	0.208	0.91	21.0	DGG
B92303/Tudor®	0.067	0.91	3.0	DGG
B93144/Ground	0.39	0.88	43.0	RB
B93184/Tudor®	0.24	0.93	25.0	DGG
B93296/Tudor®	0.218	0.92	23.0	RB

PREST® BRICK

Brick Color and Finish	Reflect. Average	Emitt. Average	SRI	Color
B93409/Tudor®	0.432	0.94	51.0	RB
Brown/Tudor®	0.258	0.93	28.0	RB
Charcoal/Tudor®	0.232	0.91	24.0	DGG
Cream/Tudor®	0.25	0.91	26.0	WL
Gettysburg Gray/Tumbled	0.208	0.93	22.0	LMG
Limestone Gray/Tudor®	0.32	0.93	36.0	LMG
Limestone Gray/Natural	0.165	0.94	17.0	LMG
Natural Charcoal/Tudor®	0.27	0.91	29.0	LMG
Natural/Natural	0.22	0.93	23.0	LMG
Natural/Tudor®	0.316	0.93	35.0	LMG
Red Charcoal Blend/ Natural	0.17	0.95	18.0	RB
Salmon Charcoal Blend/ Tumbled	0.293	0.89	31.0	RB
Tan/Tudor®	0.28	0.90	30.0	BT
Tan/Natural	0.21	0.90	20.0	BT
Antietam/Tudor®	0.309	0.95	35.0	BT
Antietam/Ground Tudor®	0.329	0.92	37.0	BT

Color Group Codes

WL = White to Light Buffs and Grays
 BT = Buff to Tan
 LMG = Light Gray to Medium Gray
 DGG = Dark Gray to Green
 RB = Red to Brown